



# THEORY OF PLASTIC FLOW II

**Jiří Plešek**

Institute of Thermomechanics  
Czech Academy of Sciences



# Contents

---

- Review of  $J_2$  theory
- Hugoniot problem
- Validation
- Fathers of plasticity



# Review of $J_2$ -theory

---

Von Mises stress

$$\sigma_e = \sqrt{\frac{3}{2} S_{ij} S_{ij}} \Rightarrow F(\sigma_{ij}) = \sigma_e - \sigma_Y \leq 0$$



# Review of $J_2$ -theory

---

Von Mises stress

$$\sigma_e = \sqrt{\frac{3}{2} S_{ij} S_{ij}} \Rightarrow F(\sigma_{ij}) = \sigma_e - \sigma_Y \leq 0$$

Associated flow rule

$$\dot{\epsilon}_{ij}^p = \lambda \frac{\partial F}{\partial \sigma_{ij}} = \frac{3}{2} \frac{\lambda}{\sigma_Y} S_{ij} \quad (\text{deviatoric})$$



# Review of $J_2$ -theory

---

Von Mises stress

$$\sigma_e = \sqrt{\frac{3}{2} S_{ij} S_{ij}} \Rightarrow F(\sigma_{ij}) = \sigma_e - \sigma_Y \leq 0$$

Associated flow rule

$$\dot{\epsilon}_{ij}^p = \lambda \frac{\partial F}{\partial \sigma_{ij}} = \frac{3}{2} \frac{\lambda}{\sigma_Y} S_{ij} \quad (\text{deviatoric})$$

Plastic multiplier

$$\lambda = \frac{S_{ij} \dot{\epsilon}_{ij}}{\sigma_Y} \quad (\text{from consistency condition } \dot{F} = 0)$$



# Review of $J_2$ -theory

---

Von Mises stress

$$\sigma_e = \sqrt{\frac{3}{2} S_{ij} S_{ij}} \Rightarrow F(\sigma_{ij}) = \sigma_e - \sigma_Y \leq 0$$

Associated flow rule

$$\dot{\epsilon}_{ij}^p = \lambda \frac{\partial F}{\partial \sigma_{ij}} = \frac{3}{2} \frac{\lambda}{\sigma_Y} S_{ij} \quad (\text{deviatoric})$$

Plastic multiplier

$$\lambda = \frac{S_{ij} \dot{\epsilon}_{ij}}{\sigma_Y} \quad (\text{from consistency condition } \dot{F} = 0)$$

Stress update


$$\dot{\sigma}_{ij} = C_{ijkl}(\dot{\epsilon}_{kl} - \dot{\epsilon}_{kl}^p) = \dot{\sigma}_{ij}^t - 2G\dot{\epsilon}_{ij}^p$$






# Hugoniot problem (1/3)

---



# Hugoniot problem (1/3)




Stress tensor

$$\sigma = \begin{bmatrix} \sigma_o & 0 & 0 \\ 0 & \sigma_r & 0 \\ 0 & 0 & \sigma_r \end{bmatrix} \quad (\mu_\sigma = \pm 1)$$



# Hugoniot problem (1/3)




Stress tensor

$$\sigma = \begin{bmatrix} \sigma_o & 0 & 0 \\ 0 & \sigma_r & 0 \\ 0 & 0 & \sigma_r \end{bmatrix} \quad (\mu_\sigma = \pm 1)$$

Universal yield condition

$$\sigma_e = \tau_e = |\sigma_o - \sigma_r| = \sigma_Y$$

# Hugoniot problem (1/3)



Stress tensor

$$\sigma = \begin{bmatrix} \sigma_o & 0 & 0 \\ 0 & \sigma_r & 0 \\ 0 & 0 & \sigma_r \end{bmatrix} \quad (\mu_\sigma = \pm 1)$$


Universal yield condition

$$\sigma_e = \tau_e = |\sigma_o - \sigma_r| = \sigma_Y$$

Boundary condition for elastic state

$$E\epsilon_r^e = \sigma_r - \nu(\sigma_o + \sigma_r) = 0$$

# Hugoniot problem (1/3)



Stress tensor

$$\boldsymbol{\sigma} = \begin{bmatrix} \sigma_o & 0 & 0 \\ 0 & \sigma_r & 0 \\ 0 & 0 & \sigma_r \end{bmatrix} \quad (\mu_\sigma = \pm 1)$$

Universal yield condition

$$\sigma_e = \tau_e = |\sigma_o - \sigma_r| = \sigma_Y$$

Boundary condition for elastic state

$$E\epsilon_r^e = \sigma_r - \nu(\sigma_o + \sigma_r) = 0$$

Hugoniot elastic limit (HEL)

$$p = |\sigma_o| = \frac{1 - \nu}{1 - 2\nu} \sigma_Y$$



# Hugoniot problem (1/3)

---

Stress tensor

$$\boldsymbol{\sigma} = \begin{bmatrix} \sigma_o & 0 & 0 \\ 0 & \sigma_r & 0 \\ 0 & 0 & \sigma_r \end{bmatrix} \quad (\mu_\sigma = \pm 1)$$

Stress deviator

$$\mathbf{S} = \begin{bmatrix} S_o & 0 & 0 \\ 0 & S_r & 0 \\ 0 & 0 & S_r \end{bmatrix}$$

Universal yield condition

$$\sigma_e = \tau_e = |\sigma_o - \sigma_r| = \sigma_Y$$

Boundary condition for elastic state

$$E\epsilon_r^e = \sigma_r - \nu(\sigma_o + \sigma_r) = 0$$

Hugoniot elastic limit (HEL)

$$p = |\sigma_o| = \frac{1 - \nu}{1 - 2\nu} \sigma_Y$$



# Hugoniot problem (1/3)

---

Stress tensor

$$\boldsymbol{\sigma} = \begin{bmatrix} \sigma_o & 0 & 0 \\ 0 & \sigma_r & 0 \\ 0 & 0 & \sigma_r \end{bmatrix} \quad (\mu_\sigma = \pm 1)$$

Universal yield condition

$$\sigma_e = \tau_e = |\sigma_o - \sigma_r| = \sigma_Y$$

Boundary condition for elastic state

$$E\epsilon_r^e = \sigma_r - \nu(\sigma_o + \sigma_r) = 0$$

Hugoniot elastic limit (HEL)

$$p = |\sigma_o| = \frac{1 - \nu}{1 - 2\nu} \sigma_Y$$

Stress deviator

$$\mathbf{S} = \begin{bmatrix} S_o & 0 & 0 \\ 0 & S_r & 0 \\ 0 & 0 & S_r \end{bmatrix}$$

Zero trace theorem

$$S_o + S_r + S_r = 0$$





# Hugoniot problem (1/3)

---

Stress tensor

$$\boldsymbol{\sigma} = \begin{bmatrix} \sigma_o & 0 & 0 \\ 0 & \sigma_r & 0 \\ 0 & 0 & \sigma_r \end{bmatrix} \quad (\mu_\sigma = \pm 1)$$

Universal yield condition

$$\sigma_e = \tau_e = |\sigma_o - \sigma_r| = \sigma_Y$$

Boundary condition for elastic state

$$E\epsilon_r^e = \sigma_r - \nu(\sigma_o + \sigma_r) = 0$$

Hugoniot elastic limit (HEL)

$$p = |\sigma_o| = \frac{1 - \nu}{1 - 2\nu} \sigma_Y$$

Stress deviator

$$\mathbf{S} = \begin{bmatrix} S_o & 0 & 0 \\ 0 & S_r & 0 \\ 0 & 0 & S_r \end{bmatrix}$$

Zero trace theorem

$$S_o + S_r + S_r = 0$$

Stress deviator

$$\mathbf{S} = \frac{S_o}{2} \begin{bmatrix} 2 & 0 & 0 \\ 0 & -1 & 0 \\ 0 & 0 & -1 \end{bmatrix}$$



# Hugoniot problem (1/3)

---

Stress tensor

$$\boldsymbol{\sigma} = \begin{bmatrix} \sigma_o & 0 & 0 \\ 0 & \sigma_r & 0 \\ 0 & 0 & \sigma_r \end{bmatrix} \quad (\mu_\sigma = \pm 1)$$

Universal yield condition

$$\sigma_e = \tau_e = |\sigma_o - \sigma_r| = \sigma_Y$$

Boundary condition for elastic state

$$E\epsilon_r^e = \sigma_r - \nu(\sigma_o + \sigma_r) = 0$$

Hugoniot elastic limit (HEL)

$$p = |\sigma_o| = \frac{1 - \nu}{1 - 2\nu} \sigma_Y$$

Stress deviator

$$\mathbf{S} = \begin{bmatrix} S_o & 0 & 0 \\ 0 & S_r & 0 \\ 0 & 0 & S_r \end{bmatrix}$$

Zero trace theorem

$$S_o + S_r + S_r = 0$$

Stress deviator

$$\mathbf{S} = \frac{S_o}{2} \underbrace{\begin{bmatrix} 2 & 0 & 0 \\ 0 & -1 & 0 \\ 0 & 0 & -1 \end{bmatrix}}_{\mathbf{M}}$$



# Hugoniot problem (1/3)

---

Stress deviator

$$\mathbf{S} = \begin{bmatrix} S_o & 0 & 0 \\ 0 & S_r & 0 \\ 0 & 0 & S_r \end{bmatrix}$$

Zero trace theorem

$$S_o + S_r + S_r = 0$$

Stress deviator

$$\mathbf{S} = \frac{S_o}{2} \underbrace{\begin{bmatrix} 2 & 0 & 0 \\ 0 & -1 & 0 \\ 0 & 0 & -1 \end{bmatrix}}_{\mathbf{M}}$$

Yield condition

$$|S_o - S_r| = \frac{|S_o|}{2}(2 + 1) = \sigma_Y$$



# Hugoniot problem (1/3)

---

Stress deviator

$$\mathbf{S} = \begin{bmatrix} S_o & 0 & 0 \\ 0 & S_r & 0 \\ 0 & 0 & S_r \end{bmatrix}$$

Zero trace theorem

$$S_o + S_r + S_r = 0$$

Stress deviator

$$\mathbf{S} = \frac{S_o}{2} \underbrace{\begin{bmatrix} 2 & 0 & 0 \\ 0 & -1 & 0 \\ 0 & 0 & -1 \end{bmatrix}}_{\mathbf{M}}$$

Yield condition

$$|S_o - S_r| = \frac{|S_o|}{2}(2 + 1) = \sigma_Y$$

therefore

$$S_o = -\frac{2}{3}\sigma_Y$$



# Hugoniot problem (1/3)

---

Stress deviator

$$\mathbf{S} = \begin{bmatrix} S_o & 0 & 0 \\ 0 & S_r & 0 \\ 0 & 0 & S_r \end{bmatrix}$$

Zero trace theorem

$$S_o + S_r + S_r = 0$$

Stress deviator

$$\mathbf{S} = \frac{S_o}{2} \underbrace{\begin{bmatrix} 2 & 0 & 0 \\ 0 & -1 & 0 \\ 0 & 0 & -1 \end{bmatrix}}_{\mathbf{M}}$$

Yield condition

$$|S_o - S_r| = \frac{|S_o|}{2}(2 + 1) = \sigma_Y$$

therefore

$$S_o = -\frac{2}{3}\sigma_Y$$

and

$$\mathbf{S} = -\frac{\sigma_Y}{3}\mathbf{M}$$

Remark: Note that the deviator tensor is constant at plastic state.





# Hugoniot problem (2/3)

---

Prandtl-Reuss

$$\dot{\epsilon}^p = \frac{3}{2} \frac{\lambda}{\sigma_Y} \mathbf{S} = -\frac{\lambda}{2} \mathbf{M}$$



# Hugoniot problem (2/3)

---

Prandtl-Reuss

$$\dot{\epsilon}^p = \frac{3}{2} \frac{\lambda}{\sigma_Y} \mathbf{S} = -\frac{\lambda}{2} \mathbf{M}$$

Plastic multiplier

$$\lambda = \frac{S_{ij} \dot{\epsilon}_{ij}}{\sigma_Y}$$



# Hugoniot problem (2/3)

---

Prandtl-Reuss

$$\dot{\epsilon}^p = \frac{3}{2} \frac{\lambda}{\sigma_Y} \mathbf{S} = -\frac{\lambda}{2} \mathbf{M}$$

Plastic multiplier

$$\lambda = \frac{S_{ij} \dot{\epsilon}_{ij}}{\sigma_Y} = \frac{S_o \dot{\epsilon}_o}{\sigma_Y}$$



## Hugoniot problem (2/3)

---

Prandtl-Reuss

$$\dot{\epsilon}^p = \frac{3}{2} \frac{\lambda}{\sigma_Y} \mathbf{S} = -\frac{\lambda}{2} \mathbf{M}$$

Plastic multiplier

$$\lambda = \frac{S_{ij} \dot{\epsilon}_{ij}}{\sigma_Y} = \frac{S_o \dot{\epsilon}_o}{\sigma_Y} = -\frac{2}{3} \dot{\epsilon}_o$$



## Hugoniot problem (2/3)

---

Prandtl-Reuss

$$\dot{\epsilon}^p = \frac{3}{2} \frac{\lambda}{\sigma_Y} \mathbf{S} = -\frac{\lambda}{2} \mathbf{M}$$

Plastic multiplier

$$\lambda = \frac{S_{ij} \dot{\epsilon}_{ij}}{\sigma_Y} = \frac{S_o \dot{\epsilon}_o}{\sigma_Y} = -\frac{2}{3} \dot{\epsilon}_o$$

Plastic strain rate

$$\dot{\epsilon}^p = \frac{\dot{\epsilon}_o}{3} \mathbf{M}$$





# Hugoniot problem (2/3)

---

Prandtl-Reuss

$$\dot{\epsilon}^p = \frac{3}{2} \frac{\lambda}{\sigma_Y} \mathbf{S} = -\frac{\lambda}{2} \mathbf{M}$$

Plastic multiplier

$$\lambda = \frac{S_{ij} \dot{\epsilon}_{ij}}{\sigma_Y} = \frac{S_o \dot{\epsilon}_o}{\sigma_Y} = -\frac{2}{3} \dot{\epsilon}_o$$

Plastic strain rate

$$\dot{\epsilon}^p = \frac{\dot{\epsilon}_o}{3} \mathbf{M}$$

Integrating

$$\Delta \epsilon^p = \frac{\Delta \epsilon_o}{3} \mathbf{M}$$



## Hugoniot problem (2/3)

---

Prandtl-Reuss

$$\dot{\epsilon}^p = \frac{3}{2} \frac{\lambda}{\sigma_Y} \mathbf{S} = -\frac{\lambda}{2} \mathbf{M}$$

Plastic multiplier

$$\lambda = \frac{S_{ij} \dot{\epsilon}_{ij}}{\sigma_Y} = \frac{S_o \dot{\epsilon}_o}{\sigma_Y} = -\frac{2}{3} \dot{\epsilon}_o$$

Plastic strain rate

$$\dot{\epsilon}^p = \frac{\dot{\epsilon}_o}{3} \mathbf{M}$$

Integrating

$$\Delta \epsilon^p = \frac{\Delta \epsilon_o}{3} \mathbf{M}$$

Axial strain

$$\Delta \epsilon_o^e = \Delta \epsilon_o - \Delta \epsilon_o^p = \frac{1}{3} \Delta \epsilon_o$$



## Hugoniot problem (2/3)

---

Prandtl-Reuss

$$\dot{\epsilon}^p = \frac{3}{2} \frac{\lambda}{\sigma_Y} \mathbf{S} = -\frac{\lambda}{2} \mathbf{M}$$

Plastic multiplier

$$\lambda = \frac{S_{ij} \dot{\epsilon}_{ij}}{\sigma_Y} = \frac{S_o \dot{\epsilon}_o}{\sigma_Y} = -\frac{2}{3} \dot{\epsilon}_o$$

Plastic strain rate

$$\dot{\epsilon}^p = \frac{\dot{\epsilon}_o}{3} \mathbf{M}$$

Integrating

$$\Delta \epsilon^p = \frac{\Delta \epsilon_o}{3} \mathbf{M}$$

Axial strain

$$\Delta \epsilon_o^e = \Delta \epsilon_o - \Delta \epsilon_o^p = \frac{1}{3} \Delta \epsilon_o$$

Radial strain

$$\Delta \epsilon_r^e = 0 - \Delta \epsilon_r^p = \frac{1}{3} \Delta \epsilon_o$$

## Hugoniot problem (2/3)

---

Prandtl-Reuss

$$\dot{\epsilon}^p = \frac{3}{2} \frac{\lambda}{\sigma_Y} \mathbf{S} = -\frac{\lambda}{2} \mathbf{M}$$

Plastic multiplier

$$\lambda = \frac{S_{ij} \dot{\epsilon}_{ij}}{\sigma_Y} = \frac{S_o \dot{\epsilon}_o}{\sigma_Y} = -\frac{2}{3} \dot{\epsilon}_o$$

Plastic strain rate

$$\dot{\epsilon}^p = \frac{\dot{\epsilon}_o}{3} \mathbf{M}$$

Integrating

$$\Delta \epsilon^p = \frac{\Delta \epsilon_o}{3} \mathbf{M}$$

Axial strain

$$\Delta \epsilon_o^e = \Delta \epsilon_o - \Delta \epsilon_o^p = \frac{1}{3} \Delta \epsilon_o$$

Radial strain

$$\Delta \epsilon_r^e = 0 - \Delta \epsilon_r^p = \frac{1}{3} \Delta \epsilon_o$$

Elastic strain tensor

$$\Delta \epsilon^e = \frac{1}{3} \Delta \epsilon_o \mathbf{I} \quad (\text{isotropic})$$



## Hugoniot problem (2/3)

---

Prandtl-Reuss

$$\dot{\epsilon}^p = \frac{3}{2} \frac{\lambda}{\sigma_Y} \mathbf{S} = -\frac{\lambda}{2} \mathbf{M}$$

Plastic multiplier

$$\lambda = \frac{S_{ij} \dot{\epsilon}_{ij}}{\sigma_Y} = \frac{S_o \dot{\epsilon}_o}{\sigma_Y} = -\frac{2}{3} \dot{\epsilon}_o$$

Plastic strain rate

$$\dot{\epsilon}^p = \frac{\dot{\epsilon}_o}{3} \mathbf{M}$$

Integrating

$$\Delta \epsilon^p = \frac{\Delta \epsilon_o}{3} \mathbf{M}$$

Axial strain

$$\Delta \epsilon_o^e = \Delta \epsilon_o - \Delta \epsilon_o^p = \frac{1}{3} \Delta \epsilon_o$$

Radial strain

$$\Delta \epsilon_r^e = 0 - \Delta \epsilon_r^p = \frac{1}{3} \Delta \epsilon_o$$

Elastic strain tensor

$$\Delta \epsilon^e = \frac{1}{3} \Delta \epsilon_o \mathbf{I} \quad (\text{isotropic})$$

Hydrostatic pressure


$$-\Delta p = K \Delta \epsilon_o$$






## Hugoniot problem (3/3)

---



(no plastic collapse)

# Hugoniot problem (3/3)



(no plastic collapse)

Hugoniot elastic limit

$$HEL = \frac{1 - \nu}{1 - 2\nu} \sigma_Y \simeq 1.75 \sigma_Y$$

Bulk sound speed

$$c_0 = \sqrt{\frac{K}{\rho_0}}$$

Hugoniot empirical relation

$$c = c_0 + sv \quad (\text{for most metals: } s \simeq 1.5)$$

Remark: Used in the hydrodynamic approximation of shock waves.



# Taylor & Quinney (1931)

---

Lode's parameter

$$\mu_{\sigma} = \frac{\sigma_2 - (\sigma_1 + \sigma_3)/2}{(\sigma_1 - \sigma_3)/2}$$



# Taylor & Quinney (1931)

---

Lode's parameter

$$\mu_{\sigma} = \frac{\sigma_2 - (\sigma_1 + \sigma_3)/2}{(\sigma_1 - \sigma_3)/2} = \frac{2\sigma_2 - (\sigma_1 + \sigma_3)}{\sigma_1 - \sigma_3}$$



# Taylor & Quinney (1931)

---

Lode's parameter

$$\mu_{\sigma} = \frac{\sigma_2 - (\sigma_1 + \sigma_3)/2}{(\sigma_1 - \sigma_3)/2} = \frac{2\sigma_2 - (\sigma_1 + \sigma_3)}{\sigma_1 - \sigma_3} = \frac{3S_2}{S_1 - S_3}$$





# Taylor & Quinney (1931)

---

Lode's parameter

$$\mu_{\sigma} = \frac{\sigma_2 - (\sigma_1 + \sigma_3)/2}{(\sigma_1 - \sigma_3)/2} = \frac{2\sigma_2 - (\sigma_1 + \sigma_3)}{\sigma_1 - \sigma_3} = \frac{3S_2}{S_1 - S_3}$$

Analogically

$$\mu_{\dot{\epsilon}^p} = \frac{3\dot{\epsilon}_2^p}{\dot{\epsilon}_1^p - \dot{\epsilon}_3^p}$$



# Taylor & Quinney (1931)

---

Lode's parameter

$$\mu_{\sigma} = \frac{\sigma_2 - (\sigma_1 + \sigma_3)/2}{(\sigma_1 - \sigma_3)/2} = \frac{2\sigma_2 - (\sigma_1 + \sigma_3)}{\sigma_1 - \sigma_3} = \frac{3S_2}{S_1 - S_3}$$

Analogically

$$\mu_{\dot{\epsilon}^p} = \frac{3\dot{\epsilon}_2^p}{\dot{\epsilon}_1^p - \dot{\epsilon}_3^p} = \frac{3S_2}{S_1 - S_3} = \mu_{\sigma}$$



# Taylor & Quinney (1931)

---

Lode's parameter


$$\mu_{\sigma} = \frac{\sigma_2 - (\sigma_1 + \sigma_3)/2}{(\sigma_1 - \sigma_3)/2} = \frac{2\sigma_2 - (\sigma_1 + \sigma_3)}{\sigma_1 - \sigma_3} = \frac{3S_2}{S_1 - S_3}$$

Analogically

$$\mu_{\dot{\epsilon}^p} = \frac{3\dot{\epsilon}_2^p}{\dot{\epsilon}_1^p - \dot{\epsilon}_3^p} = \frac{3S_2}{S_1 - S_3} = \mu_{\sigma}$$


Thus, we need to test

$$\mu_{\dot{\epsilon}^p} = \mu_{\sigma} \quad \text{for } \mu \in [-1, 0]$$



Experimentální ověření závislosti

$$\nu_\sigma = \nu_\epsilon$$



**FIG. 8. Experimental results of Taylor and Quinney from combined torsion and tension tests on thin-walled tubes ( $\mu$  and  $\nu$  are Lode's variables).**





# Lode & Nádai (1928)

---

Proportional loading

$$\mathbf{S}(t) = g(t)\mathbf{S}^0$$



# Lode & Nádai (1928)

---

Proportional loading

$$\mathbf{S}(t) = g(t)\mathbf{S}^0$$

Prandtl-Reuss equation

$$\dot{\epsilon}^p = \lambda_p \mathbf{S} = \lambda_p g(t) \mathbf{S}^0$$



# Lode & Nádai (1928)

---

Proportional loading

$$\mathbf{S}(t) = g(t)\mathbf{S}^0$$

Prandtl-Reuss equation

$$\dot{\epsilon}^p = \lambda_p \mathbf{S} = \lambda_p g(t) \mathbf{S}^0$$

Integration

$$\epsilon^p = h(t) \mathbf{S}^0 = \frac{h(t)}{g(t)} \mathbf{S} = \lambda_H \mathbf{S} \quad (\text{Hencky, 1924})$$



# Lode & Nádai (1928)

---

Proportional loading

$$\mathbf{S}(t) = g(t)\mathbf{S}^0$$

Prandtl-Reuss equation


$$\dot{\epsilon}^p = \lambda_p \mathbf{S} = \lambda_p g(t) \mathbf{S}^0$$

Integration

$$\epsilon^p = h(t) \mathbf{S}^0 = \frac{h(t)}{g(t)} \mathbf{S} = \lambda_H \mathbf{S} \quad (\text{Hencky, 1924})$$

Therefore

$$\mu_{\epsilon^p} = \mu_{\sigma} \quad \text{for } \mu \in [-1, 1]$$



Experimentální ověření závislosti

$$\nu_\sigma = \nu_\epsilon$$





# Discussion of the controversy

---

Assuming linearity of the flow rule

$$\dot{\epsilon}^p = \lambda \mathcal{L}(\sigma)$$



# Discussion of the controversy

---

Assuming linearity of the flow rule

$$\dot{\epsilon}^p = \lambda \mathcal{L}(\sigma)$$

Assuming isotropy

$$\dot{\epsilon}_1^p = A\sigma_1 + B\sigma_2 + B\sigma_3$$

$$\dot{\epsilon}_2^p = B\sigma_1 + A\sigma_2 + B\sigma_3$$

$$\dot{\epsilon}_3^p = B\sigma_1 + B\sigma_2 + A\sigma_3$$



# Discussion of the controversy

---

Assuming linearity of the flow rule

$$\dot{\epsilon}^p = \lambda \mathcal{L}(\sigma)$$

Assuming isotropy

$$\dot{\epsilon}_1^p = A\sigma_1 + B\sigma_2 + B\sigma_3$$

$$\dot{\epsilon}_2^p = B\sigma_1 + A\sigma_2 + B\sigma_3$$

$$\dot{\epsilon}_3^p = B\sigma_1 + B\sigma_2 + A\sigma_3$$

Mean strain

$$\dot{\epsilon}_m^p = A\sigma_m + 2B\sigma_m$$



# Discussion of the controversy

---

Assuming linearity of the flow rule

$$\dot{\epsilon}^p = \lambda \mathcal{L}(\sigma)$$

Assuming isotropy

$$\dot{\epsilon}_1^p = A\sigma_1 + B\sigma_2 + B\sigma_3$$

$$\dot{\epsilon}_2^p = B\sigma_1 + A\sigma_2 + B\sigma_3$$

$$\dot{\epsilon}_3^p = B\sigma_1 + B\sigma_2 + A\sigma_3$$

Mean strain

$$\dot{\epsilon}_m^p = A\sigma_m + 2B\sigma_m$$

Assuming incompressibility

$$2B = -A$$



# Discussion of the controversy

---

Assuming linearity of the flow rule

$$\dot{\epsilon}^p = \lambda \mathcal{L}(\sigma)$$

Assuming isotropy

$$\dot{\epsilon}_1^p = A\sigma_1 + B\sigma_2 + B\sigma_3$$

$$\dot{\epsilon}_2^p = B\sigma_1 + A\sigma_2 + B\sigma_3$$

$$\dot{\epsilon}_3^p = B\sigma_1 + B\sigma_2 + A\sigma_3$$

Mean strain

$$\dot{\epsilon}_m^p = A\sigma_m + 2B\sigma_m$$

Assuming incompressibility

$$2B = -A$$

Thus, we have

$$2\dot{\epsilon}_1^p = A(2\sigma_1 - (\sigma_2 + \sigma_3))$$

$$2\dot{\epsilon}_2^p = A(2\sigma_2 - (\sigma_1 + \sigma_3))$$

$$2\dot{\epsilon}_3^p = A(2\sigma_3 - (\sigma_1 + \sigma_2))$$





# Discussion of the controversy

---

Assuming linearity of the flow rule

$$\dot{\epsilon}^p = \lambda \mathcal{L}(\sigma)$$

Assuming isotropy

$$\dot{\epsilon}_1^p = A\sigma_1 + B\sigma_2 + B\sigma_3$$

$$\dot{\epsilon}_2^p = B\sigma_1 + A\sigma_2 + B\sigma_3$$

$$\dot{\epsilon}_3^p = B\sigma_1 + B\sigma_2 + A\sigma_3$$

Mean strain

$$\dot{\epsilon}_m^p = A\sigma_m + 2B\sigma_m$$

Assuming incompressibility

$$2B = -A$$

Thus, we have

$$2\dot{\epsilon}_1^p = A(2\sigma_1 - (\sigma_2 + \sigma_3))$$

$$2\dot{\epsilon}_2^p = A(2\sigma_2 - (\sigma_1 + \sigma_3))$$

$$2\dot{\epsilon}_3^p = A(2\sigma_3 - (\sigma_1 + \sigma_2))$$

Deviator completion

$$2\dot{\epsilon}_1^p = 3AS_1$$

$$2\dot{\epsilon}_2^p = 3AS_2$$

$$2\dot{\epsilon}_3^p = 3AS_3$$



# Discussion of the controversy

---

Assuming linearity of the flow rule

$$\dot{\epsilon}^p = \lambda \mathcal{L}(\sigma)$$

Assuming isotropy

$$\begin{aligned}\dot{\epsilon}_1^p &= A\sigma_1 + B\sigma_2 + B\sigma_3 \\ \dot{\epsilon}_2^p &= B\sigma_1 + A\sigma_2 + B\sigma_3 \\ \dot{\epsilon}_3^p &= B\sigma_1 + B\sigma_2 + A\sigma_3\end{aligned}$$

Mean strain

$$\dot{\epsilon}_m^p = A\sigma_m + 2B\sigma_m$$

Assuming incompressibility

$$2B = -A$$

Thus, we have

$$\begin{aligned}2\dot{\epsilon}_1^p &= A(2\sigma_1 - (\sigma_2 + \sigma_3)) \\ 2\dot{\epsilon}_2^p &= A(2\sigma_2 - (\sigma_1 + \sigma_3)) \\ 2\dot{\epsilon}_3^p &= A(2\sigma_3 - (\sigma_1 + \sigma_2))\end{aligned}$$

Deviator completion

$$\begin{aligned}2\dot{\epsilon}_1^p &= 3AS_1 \\ 2\dot{\epsilon}_2^p &= 3AS_2 \\ 2\dot{\epsilon}_3^p &= 3AS_3\end{aligned}$$

Therefore

$$\dot{\epsilon}^p = \lambda_p \mathbf{S}$$



# Discussion of the controversy

---

Assuming linearity of the flow rule

$$\dot{\epsilon}^p = \lambda \mathcal{L}(\boldsymbol{\sigma})$$

Assuming isotropy

$$\begin{aligned}\dot{\epsilon}_1^p &= A\sigma_1 + B\sigma_2 + B\sigma_3 \\ \dot{\epsilon}_2^p &= B\sigma_1 + A\sigma_2 + B\sigma_3 \\ \dot{\epsilon}_3^p &= B\sigma_1 + B\sigma_2 + A\sigma_3\end{aligned}$$

Mean strain

$$\dot{\epsilon}_m^p = A\sigma_m + 2B\sigma_m$$

Assuming incompressibility

$$2B = -A$$

Thus, we have

$$\begin{aligned}2\dot{\epsilon}_1^p &= A(2\sigma_1 - (\sigma_2 + \sigma_3)) \\ 2\dot{\epsilon}_2^p &= A(2\sigma_2 - (\sigma_1 + \sigma_3)) \\ 2\dot{\epsilon}_3^p &= A(2\sigma_3 - (\sigma_1 + \sigma_2))\end{aligned}$$

Deviator completion

$$\begin{aligned}2\dot{\epsilon}_1^p &= 3AS_1 \\ 2\dot{\epsilon}_2^p &= 3AS_2 \\ 2\dot{\epsilon}_3^p &= 3AS_3\end{aligned}$$

Therefore

$$\dot{\epsilon}^p = \lambda_p \mathbf{S}$$

Conclusion: Slight non-linearity of  $\mathbf{R}(\boldsymbol{\sigma})$  is probably the culprit.



# Henri Édouard Tresca

---



(1814-1885)



# Adémar J. C. Barré de Saint-Venant

---



(1797-1886)





# Richard Edler von Mises

---



(1883-1953)